



Properties of Barrier Fleece

Determination of the Material Properties pertains to 50 % Air Humidity and $T=23\ {\rm ^oC}$.

Physical Property	Unit	Preferred Value
GSM Substance ISO 9073-1	g m ⁻²	70.0
Dry Tensile Strength (Machine Direction) ISO 9073-3	N m-1	3200
Dry Tensile Strength (Transverse Direction)	N m.¹	850
Elmendorf Tear Strength (Machine Direction) ISO 9073-4	Νm	2600
Dry Elongation (Machine Direction) ISO 9073-3	%	25
Dry Elongation (Transverse Direction) ISO 9073-3	%	100
Air Pemeability	1 min ⁻¹ 100 cm ⁻²	55-120
Water Permeability	mbar	23
Alcohol Repulsion Ability IST 80,6 - 92	graduation	01

Fig. 3